

4244Q

QUICK EXTRUDING SILANE CROSS-LINKABLE PE COMPOUND

FOR 3KV AND BELOW CABLE & WIRE

Description

Grade 4244Q is sioplas (two steps) silane XLPE compound for low voltage cable with small cross sectional area, it is composed by silane crosslinkable low density polyethylene (compound A) and silane crosslinkable catalyst (compound B). Compound A is grafted by high activity silane and special PE compound, while compound B adopts the advanced catalyst system. The product has outstanding performance and major characteristics are

- The product is suitable for the extrusion method of tubing extrusion.
- Cables made from the product have excellent performance in smooth cable surface, high extrusion speed and production efficiency.
- Suitable for cable cross-sectional area less than 16mm².
- Low processing temperature and cost saving.

Standard

Performance test is in accordance with JB/T 10437-2004 standard. After crosslinked in the tepid water, the cable made from the product grade 4244Q can comply with the standard of IEC60502-2004, GB/T12706-2002.

Main Properties & Typical Values

Test items	Test method	Unit	Standard	Typical value
Tensile strength	GB/T1040.3	MPa	≥14.0	24.5
Elongation at break	GB/T1040.3	%	≥350	556
Heat ageing properties (Test temperature 135°C, 168hr)	GB/T8815			
Maximum tensile strength change		%	±20	6.9
Maximum elongation at break change		%	±20	2.2
Heat elongation (200±3)°C x 15min x 0.2MPa)	GB/T2951			
Maximum elongation change under load		%	≤80	60
Maximum permanent elongation change after cooled		%	≤5	-4
Dielectric strength	GB/T1408.1	MV/m	≥30	43*
Volume resistance (20°C)	GB/T1410	Ω.m	≥1.0×10 ¹⁴	3.5×10 ¹⁴ *
Gel content	JB/T 10437	%	≥60	64

Typical values were tested on the 1mm sample strip by squeezing film extrusion after mixing compound of A & B (at percentage of 95:5) and be boiled in hot water at 90°C for four hours.

*Especially, these typical values were tested by press moulding sample under the condition of 180±2 °C, 15min, and pressure over 15MPa, then boiled in 90°C water for four hours.

Recommended Processing Technique

1. Extrusion Equipment

Most extruders for PVC and PE suit for 4244Q.

The recommended equipment and processing technique is as following.

Ratio of length and diameter	18—25:1
Diameter	45—120mm
Ratio of compressing	1.5—3.5
Ratio of elongation	1:1.0—1:1.5
Filtering mesh	40/60/40

2. Extruder processing temperature and other related settings

Temperature Setting: Specific processing temperature should be based on different equipment and pressing conditions, reference settings are as following:

Feeding section (°C)	Compression Section (°C)	Measurement Section (°C)	Die head and Mould (°C)
130~150	150~165	165~175	175~195

Die head setting: Tubing extrusion style

3. Crosslink

After extrusion and cooling, the cable can be cross linked by immersed in hot water (90°C) or exposed in low pressure vapour. The time required for crosslink is based on the thickness of the insulation and the coil size, the thicker the insulation and the greater the coil size, the longer the crosslink time required. The crosslink time can be calculated according to the equation of 4hr/mm for 90°C.

Please contact our customer service for more technical service.